Nanoleakage of Self Adhesive Resin Composite

Thesis

Submitted to the Faculty of Oral and Dental Medicine
Cairo University
In partial fulfillment of the requirements for the
Master degree in Operative Dentistry

By

Haytham Elsayed Ahmad Abu-Elazayem Behery
B.D.S. (2006)

Misr University for Science and Technology

Cairo University

2011G - 1432H

(وَأُنزَلُّ الله عَلَيْكَ الكِتَابَ وَالْحِكْمَة وَعَلَّمَكَ مَا لَمْ تَكُن تَعْلَمُ وَكَانَ فَضْلُ الله عَلَيْكَ عَظِيماً)

المنظمة المنظ

سورة النساء جزء من الآيه ١١٣

Supervisors

Dr. Mona Ismail Riad

Professor of Operative Dentistry
Faculty of Oral and Dental Medicine
Cairo University
(Main supervisor)

Dr. Amal Khairy Sakr
Assistant Professor of Operative Dentistry
College of Oral and Dental Surgery
Misr University for Science & Technology

Dr. Asmaa Aly Mohamed Yassen
Lecturer of Operative Dentistry
Faculty of Oral and Dental Medicine
Cairo University

Dedication

To my parents who gave me the deep and the true love.....that made me who I am.

Acknowledgments

First grace and foremost thanks to *Allah* for blessing this work until it has reached its end, as a little of his generous help throughout our life.

I would like to express my highest appreciation and deepest gratitude with all the feelings of love to *Dr. Mona Ismail Riad*, Professor of Operative Dentistry, Faculty of Oral and Dental Medicine, Cairo University, for her valuable supervision, continuous guidance, encouragement and for facilitating all the difficulties that faced me throughout this study. No words can express my sincere feelings and deep gratitude.

My deepest gratitude is extended to *Dr. Amal Khairy Sakr*, Assistant Professor of Operative Dentistry, College of Oral and Dental Surgery, Misr University for Science and Technology, for her valuable guidance, generous support and supervision.

Special thanks and heartful appreciation to *Dr. Asmaa Aly Mohamed Yassen*, Lecturer of Operative Dentistry, Faculty of Oral and Dental Medicine, Cairo University, for her constructive comments, generous help in rendering every possible service to me during every step in my work.

I would like to express my great appreciation to all the staff members of Operative Dentistry Department, Faculty of Oral and Dental Medicine, Cairo University, and College of Oral and Dental Surgery, Misr University for Science and Technology for their cooperation, support and continuous advice.

List of contents

	page
List of Tables	Ι
List of Figures	III
Introduction	1
Review of literature	3
I- Self Adhesive Flowable Resin Composite	3
II- Flowable Resin Composite	5
III- Nanoleakage evaluation	8
IV- Effect of thermocycling on nanoleakage	16
V- Effect of storage periods on nanoleakage	18
Aim of the study	24
Materials and Methods	25
I-Materials	25
II-Methods	27
Results	35
I- Quantitative nanoleakage results	35
II- ESEM Micromorphological Study (Qualitative analysis)	63
Discussion	75
Summary and Conclusion	93
References	96
Arabic summary	108

List of Tables

List of Tables

		page
Table 1:	Materials used in this study.	26
Table 2:	Variables of the study.	27
Table 3:	Interaction of variables.	28
Table 4:	Results of regression analysis of the effect of material, thermocycling, storage period and their interactions on the mean silver penetration values.	35
Table 5:	The mean, standard deviation (SD) of silver penetration values of the tested materials with and without thermocycling at each storage period.	36
Table 6:	The mean, standard deviation (SD) of silver penetration values of the tested materials.	38
Table 7:	The mean, standard deviation (SD) of silver penetration values of thermocycled and non-thermocycled specimens.	39
Table 8:	The mean, standard deviation (SD) of silver penetration values of different storage periods.	40
Table 9:	Ranking between different groups.	41
Table 10:	Results of regression analysis of the effect of material, thermocycling, storage period and their interactions on the mean silver penetration values occlusally.	43
Table 11:	The mean, standard deviation (SD) of silver penetration values occlusally of the tested materials with and without thermocycling at each storage period.	44
Table 12:	The mean, standard deviation (SD) of silver penetration values occlusally of the tested materials.	46
Table 13:	The mean, standard deviation (SD) of silver penetration values occlusally of thermocycled and non-thermocycled specimens.	47
Table 14:	The mean, standard deviation (SD) of silver penetration values occlusally of different storage periods.	48

Table 15:	Ranking between different groups occlusally.	49
Table 16:	Results of regression analysis of the effect of material, thermocycling, storage period and their interactions on the mean silver penetration values cervically.	51
Table 17:	The mean, standard deviation (SD) of silver penetration values cervically of the tested materials with and without thermocycling at each storage period.	52
Table 18:	The mean, standard deviation (SD) of silver penetration values cervically of the tested materials.	54
Table 19:	The mean, standard deviation (SD) of silver penetration values cervically of thermocycled and non-thermocycled specimens.	55
Table 20:	The mean, standard deviation (SD) of silver penetration values cervically between different storage periods.	56
Table 21:	Ranking between different groups cervically.	57
Table 22:	The mean, standard deviation (SD) of silver penetration values occlusally and cervically.	59
Table 23:	The mean, standard deviation (SD) of silver penetration values between the different interactions occlusally and cervically.	60

List of Figures

List of Figures

		page
Figure 1:	Fusio Liquid Dentin (Self Adhesive Flowable Composite).	25
Figure 2:	Filtek Z350 Flowable Resin Composite.	25
Figure 3:	Filtek Z250 Micro-hybid Resin Composite.	25
Figure 4:	Etch and rinse adhesive system.	25
Figure 5:	Tooth fixed in Hiflex thermoplastic impression compound.	29
Figure 6:	Carbide end mill.	29
Figure 7:	Carbide end mill with resin composite stopper.	29
Figure 8:	Drill press machine.	29
Figure 9:	Drill press machine with the carbide end mill during cavity preparation.	30
Figure 10:	Class V prepared cavity.	30
Figure 11:	Thermocycling machine.	32
Figure 12:	Environmental Scanning Electron Microscope (ESEM).	33
Figure 13:	Bar chart represents the mean silver peneteation values of the tested materials with and without thermocycling at each storage period.	37
Figure 14:	Bar chart represents the mean silver penetration values of the tested materials.	38
Figure 15:	Bar chart represents the mean silver penetration values with and without thermocycling.	39
Figure 16:	Bar chart represents the mean silver penetration values at the two storage periods.	40
Figure 17:	Bar chart represents ranking between different groups.	42

Figure 18:	Bar chart represents the mean silver penetration values occlusally of the tested materials with and without thermocycling at each storage period.	45
Figure 19:	Bar chart represents the mean silver penetration penetration values occlusally of the tested materials.	46
Figure 20:	Bar chart represents the mean silver penetration values occlusally with and without thermocycling.	47
Figure 21:	Bar chart represents the mean silver penetration values occlusally at the two storage periods.	48
Figure 22:	Bar chart represents ranking between different groups occlusally.	50
Figure 23:	Bar chart represents the mean silver penetration values cervically of the tested restorative materials with and without thermocycling at each storage period.	53
Figure 24:	Bar chart represents the mean silver penetration values cervically of the tested restorative materials.	54
Figure 25	Bar chart represents the mean silver penetration values cervically with and without thermocycling.	55
Figure 26:	Bar chart represents the mean silver penetration values cervically at the two storage periods.	56
Figure 27:	Bar chart represents ranking between different groups cervically.	58
Figure 28:	Bar chart represents an overall comparison between mean silver penetration values of occlusal and cervical nanoleakage.	59
Figure 29:	Bar chart represents the mean silver penetration values occlusally and cervically.	62
Figure 30:	ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point occlusally at the dentin Self adhesive resin composite restoration interface for group $A_1B_1T_1$ (Ag=2.99 wt %).	63
Figure 31:	ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point	63

- cervically at the dentin Self adhesive resin composite restoration interface for group $A_1B_1T_1$ (Ag=3.05 wt %).
- **Figure 32:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point cervically at the dentin Flowable resin composite restoration interface for group A₁B₁T₁ (Ag=1.84 wt %).
- **Figure 33:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point cervically at the dentin Flowable resin composite restoration For group $A_2B_1T_1$ (Ag=2.04 wt %).
- **Figure 34:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point occlusally at the dentin Micro-hybrid resin composite restoration interface for group A₃B₁T₁ (Ag=1.20 wt %).
- **Figure 35:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point cervically at the dentin Micro-hybrid resin composite restoration interface for group A₃B₁T₁ (Ag=2.21 wt %).
- **Figure 36:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point occlusally at the dentin Self adhesive resin composite restoration interface for group A₁B₂T₁ (Ag=3.68 wt %).
- **Figure 37:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point cervically at the dentin Self adhesive resin composite restoration interface for group A₁B₂T₁ (Ag=3.23 wt %).
- **Figure 38:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point occlusally at the dentin Flowable resin composite restoration interface for group A₂B₂T₁ (Ag=2.67 wt %).
- **Figure 39:** ESEM micrograph, its corresponding EDAX spectrum curve and element analysis table for one selected point occlusally at the dentin Flowable resin composite restoration interface for group A₂B₂T₁ (Ag=3.51 wt %).