

**Chemical and Physical Studies On Some Phosphate
Glasses Containing Copper Ions**

A Thesis

Submitted to

The Chemistry Department

Faculty of Science

Ain Shams University

By

EZZ EL-DIN SOBHY METWALY

(M.Sc.)

For


The Degree of Doctor

of Philosophy

in

Chemistry

1997



Ain Shams University

Faculty of Science

Approval Sheet

Name : Ezz El-Din Sobhy Metwaly


Thesis title : Physical and chemical studies on some
phosphate glasses containing copper ions .

Supervisors

Approved

From Ain Shams University :


Dr. Ebtisam Ahmed Saad



From National Research Centre :


Prof. Dr. Morsi Mohamed Morsi

Prof. Dr. Khiry Mahmoud El Badry



Credit

Prof. Dr. A. F. Fahmy



Head of Chemistry Department



Acknowledgment

The candidate wishes to express his gratitude to Dr. Ebtisam Ahmed Saad, Chemistry Dept., Faculty of Ain Shams. For her kind interest, sincere encouragement, and advice she gave during the progress of the work.

The candidate would like to thank Prof. Dr. Morsi Mohamed Morsi, Glass Res. Dep., NRC, for supervision, suggesting. The problem, valuable discussions and his encouragement. I have learned a lot from him during the present work.

Deep appreciation to Prof. Dr. Khiry M. El-Badry, Glass Res. Dept., NRC, my promoter, for his sincere encouragement and interest and support during the present work.

My thanks also go to Dr. N. Abd El-Shafi, Researcher, Glass Res. Dept., NRC, for his interest and fruitful discussions during the work on infrared spectral data.

Special thanks are due to the president of the National research Center, Cairo for financing the thesis.

CONTENTS

Page

List of tables

List of Figures

Abstract

CHAPTER ONE

INTRODUCTION.....	1
1.1 Glass and glassy state.....	1
1.1.1 Glass formation in oxides.....	5
1.1.2 Glass compositions and structures.....	6
1.1.2.1 Silicate glasses.....	6
1.1.2.2 Borate glasses.....	11
1.2 Structures of phosphate glasses.....	15
1.2.1 Vitreous P_2O_5 (V- P_2O_5).....	15
1.2.2 Binary $M_2O + P_2O_5$ glasses.....	16
1.2.3 Q - site theory applied to phosphate glasses.....	16
1.2.4 Water in phosphate glasses	20
1.2.5 X- ray photo electron spectroscopy studies of phosphate glasses.....	21
1.2.6 Vibrational spectroscopy studies of alkali phosphate glasses.....	22
1.2.7 ^{31}P Mas-NMR studies of binary phosphate glasses	24
1.2.8 Fundamental differences between phosphate glasses and other glasses.....	26
1.3 Infrared absorption of glasses.....	27
1.4 Electrical properties.....	28
1.4.1 Mechanisms of ionic conduction.	29
1.5 Thermal expansion of glass	33
1.5.1 Methods of thermal expansion measurements.....	34
1.5.2 Thermal expansion and glass composition	34
1.6 Chemical durability	35
1.6.1 Definition	35
1.6.2 Mechanisms of durability and weatherability	36
1.6.3 Measurement of chemical durability	37
1.6.4 Factors affecting the chemical durability	38
1.6.5 Chemical durability of phosphate glasses	41
1.6.6 Dissolution mechanisms of phosphate glasses	42
1.7 Copper in glass.....	43
1.7.1 Oxidation states of copper	43
1.7.2 Colors produced by copper in glass	45
1.7.3 Distortions from perfect symmetry	46

	<i>Page</i>
CHAPTER TWO	
LITERATURE REVIEW	48
2.1 Optical studies.....	48
2.2 Electrical studies ...	50
2.3 Chemical durability and chemical analysis studies ...	55
CHAPTER THREE	
EXPERIMENTAL	58
3.1 Preparation of glass samples.....	58
3.1.1 Raw material	58
3.1.2 Melting and annealing	58
3.2 X-ray diffraction	60
3.3 Density and molar volume	60
3.4 Thermal expansion. ...	61
3.5 Infrared spectroscopy measurements.....	62
3.6 Chemical determination of Cu-ion states	62
3.6.1 Total copper determination	63
3.6.2 Determination of Cu ⁺ - ion content	63
3.6.3 Determination of Cu ²⁺ - ion content	65
3.7 ICP analysis	66
3.8 Chemical durability determination ...	66
3.8.1 Preparation of glass slabs	66
3.8.2 Procedure for determination of chemical durability	66
3.9 Electrical measurements	67
CHAPTER FOUR :	
RESULTS	69
4.1 Density and molar volume.....	69
4.1.1 Binary copper phosphate glasses.....	69
4.1.2 Ternary lead-copper phosphate glasses	69
4.1.3 Ternary zinc copper phosphate glasses	73
4.1.4 Ternary alkali and alkaline earth copper phosphate glasses	73
4.2 Thermal expansion	77
4.3 IR measurement.....	86
4.3.1 IR of binary copper phosphate glasses ..	86
4.3.2 IR of ternary lead copper phosphate glasses	86
4.3.3 IR of ternary zinc copper phosphate glasses	92
4.3.4 Ternary alkali copper metaphosphate glasses .	95

	<i>Page</i>
4.4 Chemical estimation of copper ions	98
4.4.1 Copper ions in binary copper phosphate glasses	98
4.4.2 Copper ions in ternary copper phosphate glasses	98
4.4.3 Copper ions in ternary zinc phosphate glasses	98
4.4.4 Copper ions in ternary alkali and alkaline earth copper phosphate glasses	103
4.5 Chemical durability determination	104
4.5.1 Chemical durability of binary copper phosphate glasses	104
4.5.2 Chemical durability of ternary lead copper phosphate glasses	104
4.5.3 Chemical durability of ternary zinc copper phosphate glasses	111
4.5.4 Chemical durability of ternary alkali and alkaline earth copper phosphate glasses	114
4.6 Electrical measurements	117
4.6.1 Electrical conductivity of binary copper phosphate glasses	117
4.6.2 The electrical conductivity of ternary copper containing phosphate glasses.....	117
 CHAPTER FIVE	
DISCUSSION	121
5.1 Density and molar volume.....	121
5.1.1 Binary copper phosphate glasses	122
5.1.2 Ternary lead copper phosphate glasses.....	123
5.1.3 Ternary zinc copper phosphate glasses	123
5.1.4 Ternary alkali and alkaline earth copper phosphate glasses	123
5.2 Thermal expansion	125
5.2.1 General considerations	125
5.2.2 Thermal expansion of binary copper phosphate glasses	126
5.2.3 Thermal expansion of ternary lead copper phosphate glasses	128
5.2.4 Thermal expansion of ternary zinc copper phosphate glasses	129
5.2.5 Thermal expansion of ternary alkali and alkaline earth copper phosphate glasses	130
5.3 The IR properties of copper phosphate glasses.....	131
5.3.1 Binary copper phosphate glasses	131
5.3.2 Ternary lead copper phosphate glasses	133
5.3.3 Ternary zinc copper phosphate glasses	137
5.3.4 Ternary alkali and alkali copper phosphate glasses	139
5.4 $\text{Cu}^{2+}/\text{Cu}_{\text{tot}}$ ratio in phosphate glasses.....	142
5.4.1 General consideration.....	142
5.4.1.1 Factors affecting $\text{Cu}^{2+}/\text{Cu}^+$ equilibria	142

	Page
5.4.1.2 The ellingham diagram and $\text{Cu}^{2+}/\text{Cu}^{+}$ equilibria.....	143
5.4.2 Effect of glass composition on $\text{Cu}^{2+}/\text{Cu}_{\text{tot}}$ ratios	144
5.4.2.1 Binary copper phosphate glasses	144
5.4.2.2 Ternary lead copper phosphate glasses	148
5.4.2.3 Ternary lead zinc copper phosphate glasses	148
5.4.2.4 Ternary alkali and alkaline earth copper phosphate glasses.....	149
5.5 Chemical durability	150
5.5.1 Chemical durability of binary copper phosphate glasses	150
5.5.1.1 The compositional region : $\text{P}_2\text{O}_5 \leq 50 \text{ mol\%}$	150
5.5.1.2 The compositional region : $\text{P}_2\text{O}_5 > 50 \text{ mol\%}$	152
5.5.2 Role of PbO for increasing the chemical durability of copper phosphate glasses	155
5.5.3 Effect of ZnO on the chemical durability of copper phosphate glasses.....	157
5.5.4 The chemical durability of the alkali and alkaline earth -containing copper phosphate glasses	158
5.6 Electrical conductivity	159
5.6.1 General consideration	159
5.6.2 Electrical conductivity of binary copper phosphate glasses	160
5.6.3 Electrical conductivity of ternary copper containing phosphate glasses ..	162
Summary and conclusions..	166
References	174
Arabic summary	

List of Tables

	Page
Table 1 Compositions of the glasses studied.	59
Table 2 Composition, density and molar volume of binary copper phosphate glasses studied.	70
Table 3 Composition, density and molar volume of ternary lead copper phosphate glasses studied .	70
Table 4 Composition, density and molar volume of ternary zinc copper phosphate glasses studied	74
Table 5 Composition, density and molar volume of ternary alkali and alkaline earth copper phosphate glasses studied.	74
Table 6 Thermal expansion coefficient (α), transformation temperature (T_g) and softening temperature (T_s) of some binary copper phosphate glasses .	77
Table 7 Thermal expansion coefficient (α), transformation temperature (T_g) and softening temperature (T_s) of ternary lead copper phosphate glasses .	81
Table 8 Thermal expansion coefficient (α), transformation temperature (T_g) and softening temperature (T_s) of ternary zinc copper phosphate glasses .	81
Table 9 Thermal expansion coefficient (α), transformation temperature (T_g) and softening temperature (T_s) of ternary alkali and alkaline earth copper phosphate glasses .	81
Table 10 Frequencies ranges characteristic of the IR bands related to the stretching and bending vibration of various structural groups in phosphate glasses .	88
Table 11 Frequencies of the IR active modes of binary $\text{CuO-P}_2\text{O}_5$ glasses in the 200 - 2000 cm^{-1} range.	89

Table 12	Frequencies of the IR active modes of ternary $x\text{PbO}-(50-x)\text{CuO}-50\text{P}_2\text{O}_5$ glasses in the 200 - 2000 cm^{-1} range.	91
Table 13	Frequencies of the IR active modes of ternary $x\text{ZnO}-(50-x)\text{CuO}-50\text{P}_2\text{O}_5$ glasses.	94
Table 14	Frequencies of the IR active modes of ternary $20\text{R}_2\text{O}-30\text{CuO}-50\text{P}_2\text{O}_5$ glasses.	94
Table 15	Composition , dissolution rate and $\text{Cu}^{2+}/\text{Cu}_{\text{tot}}$ ratio of binary copper phosphate glasses studied .	99
Table 16	Composition , dissolution rate and $\text{Cu}^{2+}/\text{Cu}_{\text{tot}}$ ratio of ternary lead copper phosphate glasses studied .	99
Table 17	Composition , dissolution rate and $\text{Cu}^{2+}/\text{Cu}_{\text{tot}}$ ratio of ternary zinc copper phosphate glasses studied .	101
Table 18	Composition , dissolution rate and $\text{Cu}^{2+}/\text{Cu}_{\text{tot}}$ ratio of ternary alkali and alkaline earth copper phosphate glasses studied .	101
Table 19	Weight loss per unit surface area (gm/cm^2) of binary copper phosphate glasses treated with distilled water at 70°C for different periods of time.	105
Table 20	Weight loss per unit surface area (gm/cm^2) of ternary lead copper phosphate glasses treated with distilled water at 70°C for different periods of time.	105
Table 21	Weight loss per unit surface area (gm/cm^2) of ternary zinc copper phosphate glasses treated with distilled water at 70°C for different periods of time.	110
Table 22	Weight loss per unit surface area (gm/cm^2) of ternary alkali and alkaline earth copper phosphate glasses treated with distilled water at 70°C for different periods of time.	110
Table 23	The ratios $R(=[\text{P}]/[\text{Cu}])$ of batch compositions, prepared glass samples, and solutions of corroded samples (as a result of corrosion experiment) for different copper-phosphate glasses .	151

List of Figures

		Page
Fig.1	Volume-temperature relation between the crystalline, glassy and liquid states .	3
Fig.2	Expansion of glass as a function of temperature.	3
Fig.3	(a) Basic building block for silica glass SiO_4 tetrahedra with all four oxygens bridging between neighboring tetrahedra. (b) Definition of the bond angles β and the torsion angles α_1 and α_2 (c) Schematics of the silica glass network , defining the 'bond angle' and the ring structure .	7
Fig.4	Two-dimensional representation of the structure of sodium silicate glass .	9
Fig. 5	Suggested structure of an alkali aluminosilicate glass with Al^{+3} as a network modifier showing octahedrally coordinated Al^{+3} .	11
Fig. 6	Configuration of boroxol group .	12
Fig. 7	The various borate group postulated to exist in alkali borate glasses having less than 34 mol% alkali .	12
Fig. 8	Structural models for alkali borate glasses .	12
Fig. 9	Schematic representation of the effect on the structure of phosphate glasses with the addition of alkali modifier (M_2O) .	19
Fig. 10	Composition dependence of the fraction of Q^i sites in $\text{Na}_2\text{O}+\text{H}_2\text{O} +\text{P}_2\text{O}_5$ glasses as determined by ^{31}P Mas-NMR and Raman spectroscopy .	19
Fig.11	Composition dependence of the ^{31}P Mas-NMR spectra in the series $x(\text{Na}_2\text{O}+\text{H}_2\text{O})+(1-x)\text{P}_2\text{O}_5$, where in (a) $x= 0.25$.(b) $x =0.40$ (c) $x = 0.45$, (d) = 0.5, (e) =0.53 , and (f) $x=0.56$.	25

Fig.12	Dependence of chemical shift of ^{31}P nucleus on state of depolymerization . As the P nucleus is surrounded by more nonbridging oxygens , chemical shifts move to more positive values . A similar trend is seen in silicate glasses .	25
Fig.13	A pictorial view of the A-S model	30
Fig.14	Clustering in glass at T_g showing the existence of two polymorphic structures and residual liquid; the path ways for ion migration are located in the residual liquid .	32
Fig.15	Tetragonal distortion of an octahedral d^9 - complex .	47
Fig.16	Systematic pushrod dilatometer	61
Fig.17	Three neck flask for determination of Cu^+ - ions in phosphate glasses .	65
Fig.18	DC conductivity cell (section sight)	67
Fig.19	The relation between the density and the CuO-content in the binary copper phosphate glasses .	71
Fig. 20	The relation between the molar volume and the CuO-content in binary copper phosphate glasses .	71
Fig.21	The relation between the density and the PbO content (mol%) in the ternary lead copper phosphate glasses .	72
Fig.22	The relation between the molar volume and the PbO content (mol%) in the ternary lead copper phosphate glasses .	72
Fig.23	The relation between the density and the ZnO-content (mol%) in the ternary zinc copper phosphate glasses .	75
Fig.24	The relation between the molar volume and the ZnO-content (mol%) in the ternary zinc copper phosphate glasses.	75
Fig.25	The relation between the density and R_2O or RO content (20 mol%) in the ternary $50\text{P}_2\text{O}_5$ - 30CuO - $20\text{R}_2\text{O}$ (RO) glasses .	76

Fig.26	The relation between the molar volume and R_2O or RO content (20 mol%) in the ternary $50P_2O_5-30CuO-20R_2O$ (RO) glasses .	76
Fig.27	Thermal expansion curves of binary copper phosphate glasses	78
Fig.28	Thermal expansion coefficient of copper containing phosphate glasses.	79
Fig.29	Thermal expansion curves of ternary $xPbO-(50-x) CuO- 50P_2O_5$ glasses .	82
Fig.30	Thermal expansion curves of ternary $xZnO-(50-x)CuO-50P_2O_5$ glasses .	83
Fig.31	Thermal expansion curves of ternary $50P_2O_5-30CuO- 20R_2O$ glasses, where $R_2 = Li, Na$ or K .	84
Fig.32	Thermal expansion curves of ternary $50P_2O_5-30CuO- 20RO$ glasses; where $R = Mg$ or Ca .	84
Fig.33	IR transmisssion spectra of binary $CuO-P_2O_5$ glasses .	87
Fig.34	IR transmisssion spectra of ternary $xPbO-(50-x)CuO-50P_2O_5$ glasses .	90
Fig.35	IR transmisssion spectra of ternary $xZnO-(50-x)CuO-50P_2O_5$ glasses .	93
Fig.36	IR transmisssion spectra of ternary $20R_2O-30CuO-50P_2O_5$ glasses .	96
Fig.37	Variation of $([Cu^{2+}] / [Cu_{tot.}])$ ratio as a fuction of CuO -content (mol%) in binary copper phosphate glasses .	100
Fig.38	Variation of $([Cu^{2+}] / [Cu_{tot.}])$ ratio as a function of PbO -content (mol%) in ternary lead copper phosphate glasses .	100
Fig.39	Variation of $([Cu^{2+}] / [Cu_{tot.}])$ ratio as a function of ZnO -content (mol%) in ternary zinc copper phosphate glasses .	102