



Cairo University

# **STUDYING THE EFFECT OF DIFFERENT ADDITIVES ON PHYSICAL AND MECHANICAL PROPERTIES OF MORTARS**

By

**Eng/ Amr Ramzy Abdelghany Attia**

A Thesis Submitted to the  
Faculty of Engineering at Cairo University  
In Partial Fulfillment of the  
Requirements for the Degree of  
**MASTER OF SCIENCE**  
In  
**MINING ENGINEERING**

FACULTY OF ENGINEERING, CAIRO UNIVERSITY  
GIZA, EGYPT  
2017

**STUDYING THE EFFECT OF DIFFERENT ADDITIVES  
ON PHYSICAL AND MECHANICAL PROPERTIES OF  
MORTARS**

By

**Eng/ Amr Ramzy Abdelghany Attia**

A Thesis Submitted to the  
Faculty of Engineering at Cairo University  
In Partial Fulfillment of the  
Requirements for the Degree of  
**MASTER OF SCIENCE**  
In  
**MINING ENGINEERING**

Under the Supervision of

**Prof. Dr. Salah Eldin M. Elmofty**

Professor of mineral processing  
Mining, Petroleum and Metallurgy  
Department  
Faculty of Engineering, Cairo University

**Prof. Dr. Ayman Abdel-Hamid El-Midany**

Professor of mineral processing  
Mining, Petroleum and Metallurgy  
Department  
Faculty of Engineering, Cairo University

**Prof. Dr. Mohamed kamal khallaf**

Professor of restoration  
Head of restoration department  
Faculty of Archaeology, Fayoum University

**FACULTY OF ENGINEERING, CAIRO UNIVERSITY  
GIZA, EGYPT**

2017

**STUDYING THE EFFECT OF DIFFERENT ADDITIVES  
ON PHYSICAL AND MECHANICAL PROPERTIES OF  
MORTARS**

By

**Eng/ Amr Ramzy Abdelghany Attia**

A Thesis Submitted to the  
Faculty of Engineering at Cairo University  
In Partial Fulfillment of the  
Requirements for the Degree of  
**MASTER OF SCIENCE**  
In  
**MINING ENGINEERING**

Approved by the  
Examining Committee

**Prof. Dr. Salah El-Din Mohamed El-Mofty** Thesis Main Advisor

**Prof. Dr. Ayman Abdel-Hamid El-Midany** Advisor

**Prof. Dr. Mohamed kamal khallaf** Advisor

Professor of restoration, Head of Restoration Dept., Faculty of Archaeology, Fayoum University

**Prof. Dr. Hossam Abdel-Ghafour Ahmed Hodhod** Internal Examiner

**Prof. Dr. Mostafa Ismail Gharib** External Examiner

Professor of Geochemistry, Head of Geology Dept., Faculty of Science, Helwan University.

FACULTY OF ENGINEERING, CAIRO UNIVERSITY  
GIZA, EGYPT

2017

**Engineer's Name:** Amr Ramzy Abdelghany Attia  
**Date of Birth:** 22/10/1986  
**Nationality:** Egyptian  
**E-mail:** [Eng\\_ara@yahoo.com](mailto:Eng_ara@yahoo.com)  
**Phone:** 01009904545  
**Address:** Mostay- Quesnia-Elmnoufia  
**Registration Date:** 1/10/2009  
**Awarding Date:** ..../..../2017  
**Degree:** Master of Science  
**Department:** Mining, Petroleum, and Metallurgy

**Supervisors:**

**Prof. Dr. Salah Eldeen Mohamed El-Mofty.**  
**Prof. Dr. Ayman Abdel-Hamid El-Midany.**  
**Prof. Dr. Mohamed Kamal Khallaf.**

**Examiners:**

**Prof. Dr. Salah El-Din Mohamed El-Mofty** (Thesis Main Advisor)  
Professor of mineral processing, Mining Engineering Dept., Faculty of Engineering, Cairo University.  
**Prof. Dr. Ayman Abdel-Hamid El-Midany** (Advisor)  
Professor of mineral processing, Mining Engineering Dept., Faculty of Engineering, Cairo University.  
**Prof. Dr. Mohamed kamal khallaf** (Advisor)  
Professor of restoration, Head of Restoration Dept., Faculty of Archaeology, Fayoum University.  
**Prof. Dr. Hossam Abdel-Ghafour Ahmed Hodhod** (Internal Examiner)  
Professor of Properties and Strength of Material, Structural Engineering Dept., Faculty of Engineering, Cairo University.  
**Prof. Dr. Mostafa Ismail Gharib** (External Examiner)  
Professor of Geochemistry, Head of Geology Dept., Faculty of Science, Helwan University.

**Title of Thesis:**

**STUDYING THE EFFECT OF DIFFERENT ADDITIVES ON PHYSICAL AND MECHANICAL PROPERTIES OF MORTARS**

**Key Words:**

Mortars; Additives; Mechanical properties; XRD; SEM

**Summary:**

The present work is an attempt to improve physical and mechanical properties of lime mortars by preparing mortars with adding different additives some of them are natural additives like homraa, kosromel and silica fume and the others are artificial additives from Sika Company like sika1, sikabond and sikalite. After preparation mortars, the physical and mechanical properties were measured and the samples were exposed to different environments such as Acid water weathering, Salt crystallization and Wet-dry cycle. This work is reported that polyvinyl alcohol (sikabond) improve physical and mechanical properties more than other tested additives.

## **Acknowledgments**

I would like to express my sincere gratitude to my main supervisors Prof. Dr. Salah Eldeen Mohamed Elmofty, Prof. Dr. Ayman A. El-Midany, professors of Mineral Processing, Mining, Petroleum, and Metallurgical Department, Faculty of Engineering, Cairo University and Prof. Dr. Mohamed kamal khallaf, professor of Restoration, Head of Restoration Department, Faculty of Archaeology, Fayoum University, for supporting me throughout my thesis with their patience, motivation, enthusiasm, and immense knowledge. Also for their encouragement, guidance, and kind support from the initial to the final stage.

I would like to thank Prof. Dr. Osama Hodhod, Prof. Dr. Hossam Hodhod and all the staff of Material laboratory, Civil Engineering Department, Faculty of Engineering- Cairo University.

I would like to thank all the staff of Mining Engineering Department, Faculty of Engineering- Cairo University for all their assistance and encouragement.

My special appreciation goes to my family especially my mother and my wife for everything they have done for me.

Finally, I present all my work to my father's soul.

# Table of Contents

<b>ACKNOWLEDGMENTS .....</b>	<b>I</b>
<b>TABLE OF CONTENTS.....</b>	<b>II</b>
<b>LIST OF TABLES .....</b>	<b>IV</b>
<b>LIST OF FIGURES .....</b>	<b>V</b>
<b>ABSTRACT .....</b>	<b>VIII</b>
<b>CHAPTER 1 : INTRODUCTION .....</b>	<b>1</b>
1.1.        BACKGROUND.....	1
1.2.        THESIS OBJECTIVES .....	1
<b>CHAPTER 2 : LITERATURE REVIEW .....</b>	<b>2</b>
2.1.        DEFINITION OF MORTAR.....	2
2.2.        MORTAR COMPOSITION .....	2
2.2.1.        BINDERS .....	2
2.2.1.1.    TERMINOLOGY ON LIME .....	3
2.2.2.        AGGREGATE .....	4
2.2.3.        WATER .....	4
2.2.4.        ADDITIVES AND ADMIXTURES .....	4
2.3.        TYPES OF MORTARS .....	5
2.3.1.        LIME MORTAR.....	5
2.3.1.1.    BINDER PROPERTIES.....	5
2.3.1.2.    HARDENING PROCESS .....	5
2.3.2.        HYDRAULIC MORTARS.....	6
2.3.2.1.    CEMENT MORTAR.....	7
2.3.2.1.1. <i>BINDER PROPERTIES</i> .....	7
2.3.2.1.2. <i>HARDENING PROCESS</i> .....	8
2.3.2.2.    HYDRAULIC LIME MORTAR.....	9
2.3.2.2.1. <i>BINDER PROPERTIES</i> .....	9
2.3.2.2.2. <i>HARDENING PROCESS</i> .....	10
2.3.2.3.    Pozzolanic Mortar .....	10
2.4.        DETERIORATION OF MORTARS .....	11
2.4.1.        Physical deterioration.....	11
2.4.1.1.    THE EFFECT OF WATER.....	11
2.4.1.2.    THE EFFECT OF SALTS.....	11
2.4.2.        CHEMICAL DETERIORATION.....	15
2.4.2.1.    DEGRADATION OF LIME MORTAR .....	15
2.4.2.2.    DEGRADATION OF HYDRAULIC MORTARS .....	15
2.4.3.        BIOCORROSION.....	16
2.5.        NATURAL POLYMERS AS MORTAR ADMIXTURES. ....	17
2.5.1.        OVERVIEW OF NATURAL POLYMER .....	17
2.6.        STUDYING THE EFFECT OF DIFFERENT ADDITIVES ON THE PROPERTIES OF MORTAR.....	19
<b>CHAPTER 3 : EXPERIMENTAL WORK .....</b>	<b>26</b>

3.1.	MATERIALS.....	26
3.1.1.	CHARACTERISTICS OF MATERIALS: .....	26
3.1.1.1.	CHEMICAL ANALYSIS (XRF) .....	26
3.1.1.2.	X-RAY DIFFRACTION (XRD) .....	27
3.1.1.3.	FOURIER TRANSFORM INFRARED SPECTROSCOPY .....	27
3.1.1.4.	ELECTRO-KINETIC MEASUREMENTS.....	29
3.2.	METHODS: .....	30
3.2.1.	MORTAR PREPARATION:.....	30
3.2.2.	PHYSICAL PROPERTIES.....	32
3.2.3.	MECHANICAL PROPERTIES. ....	33
3.2.4.	ARTIFICIAL AGING.....	33
3.2.4.1.	WET-DRY CYCLES. ....	33
3.2.4.2.	SALT CRYSTALLIZATION WEATHERING. ....	33
3.2.4.3.	ACID WATER WEATHERING.....	34
3.2.5.	SCANNING ELECTRON MICROSCOPY (SEM) .....	34
3.2.6.	POLARIZING MICROSCOPE.....	34
<b>CHAPTER 4 RESULTS AND DISCUSSION.....</b>		<b>35</b>
4.1.	CHARACTERISTICS OF MATERIALS USED .....	35
4.1.1.	Chemical analysis (XRF) .....	35
4.1.2.	X-RAY DIFFRACTION (XRD) .....	36
	Figures 15-18 represent the X-Ray diffraction for material used in mortar preparation as described in 3.1.1.2.....	36
4.1.3.	Fourier transform infrared spectroscopy (FTIR).....	39
4.1.4.	ELECTRO-KINETIC MEASUREMENTS.....	45
4.2.	PROPERTIES OF HARDENED MORTARS .....	50
4.2.1.	PHYSICAL PROPERTIES: .....	50
4.2.2.	MECHANICAL PROPERTIES. ....	59
4.2.2.1.	THE EFFECT OF DIFFERENT ADDITIVES ON COMPRESSIVE STRENGTH OF TESTED MORTARS. 60	
4.2.2.1.1.	<i>EFFECT OF ADDING ARTIFICIAL ADDITIVES ON MORTARS .....</i>	<i>60</i>
4.2.2.1.2.	<i>EFFECT OF ADDING NATURAL ADDITIVES ON MORTARS.....</i>	<i>61</i>
4.3.	DURABILITY (ARTIFICIAL AGEING) .....	65
4.3.1.	RESISTANCE TO WET AND DRY CYCLES .....	65
4.3.2.	RESISTANCE TO SALT CRYSTALLIZATION CYCLES .....	66
4.3.3.	RESISTANCE TO ACID WATER WEATHERING CYCLES .....	68
4.4.	SCANNING ELECTRON MICROSCOPY (SEM).....	70
4.5.	POLARIZING MICROSCOPE OBSERVATION: .....	75
<b>CONCLUSIONS.....</b>		<b>83</b>
<b>REFERENCES.....</b>		<b>84</b>

## List of Tables

Table 1: Chemical composition of clinker .....	8
Table 2: The solubility of some salts.....	13
Table 3: Crystallization pressures of some compounds .....	13
Table 4: Recrystallization pressures of some salts .....	13
Table 5: The effect of natural additives on lime mortars .....	17
Table 6: Historical overview of using natural polymers as an additives to lime mortars .....	18
Table 7 : Composition of the prepared mortars.....	30
Table 8: Chemical analysis of used additives.....	35
Table 9: density, water absorption and porosity of (lime, sand and cement) mortar .....	50
Table 10: Values of density, water absorption and porosity for all tested mortars .....	51
Table 11: Mean values of compressive strength of all tested mortars .....	59

## List of Figures

Figure 1: Lime cycle.....	6
Figure 2: Hydration heat of cement.....	9
Figure 3: Masonry damaged due to the crystallization of salt to ground water .....	14
Figure 4: Masonry damaged due to the crystallization of salt to air pollution.....	14
Figure 5: Masonry damaged due to rising water .....	14
Figure 6: Advanced axios panalytical (XRF).....	26
Figure 7: Bruker X-ray diffractometer .....	27
Figure 8: FTIR 4100 spectrometer .....	27
Figure 9: steps of preparing KBr pellet .....	28
Figure 10: Zeta meter 3.0. ....	29
Figure 11: Mortars with different mixtures during preparation .....	31
Figure 12 : Steps of physical properties measurements. ....	32
Figure 13: Compression testing machine (shimadzu- UH500 KNIR) .....	33
Figure 14: Scanning electron microscope .....	34
Figure 15: XRD pattern of Homraa.....	36
Figure 16: XRD pattern of Sikalite (P3).....	37
Figure 17: XRD pattern of Silicafume .....	37
Figure 18: XRD pattern of Kosromel.....	38
Figure 19: FTIR of used materials (a) FTIR of sand, (b) FTIR of lime, (c) FTIR of white cement, (d) FTIR of homraa, (e) FTIR of kosromel, (f) FTIR of silica fume, (g) FTIR of P1, (h) FTIR of P2, (i) FTIR of P3. ....	43
Figure 20: the behavior of zeta potential of the tested materials.....	45
Figure 21: Zeta potential of sand with additives .....	46
Figure 22: Zeta potential of white cement with additives .....	46
Figure 23: Zeta potential of Homraa with and without additives.....	47
Figure 24: Zeta potential of lime with and without additives .....	48
Figure 25: Zeta potential of silica fume with and without additives.....	48
Figure 26: Zeta potential of Kosromel with additives.....	49
Figure 27: Shows the density of mortars. (A) Density of sand, lime with and without artificial additives, (B) Density of sand, lime and homraa with and without artificial additives, (C) Density of sand, lime and kosromel with and without artificial additives, (D) Density of sand, lime and silica fume with and without artificial additives.....	53
Figure 28: Shows the water absorption of mortars. (A) Water absorption of sand, lime with and without artificial additives, (B) Water absorption of sand, lime and homraa with and without artificial additives, (C) Water absorption of sand, lime and kosromel with and without artificial additives, (D) Water absorption of sand, lime and silica fume with and without artificial additives. ....	55
Figure 29: Shows the porosity of mortars. (A) Porosity of sand, lime with and without artificial additives, (B) Porosity of sand, lime and homraa with and without artificial additives, (C) Porosity of sand, lime and kosromel with and without artificial additives, (D) Porosity of sand, lime and silica fume with and without artificial additives. ....	58
Figure 30: compressive strength of mortar sand and lime with and without artificial additives.....	60

Figure 31: compressive strength of mortar sand, lime and cement with or without artificial additives. ....	60
Figure 32 : compressive strength of mortar sand and lime with and without natural additives.....	61
Figure 33 compressive strength of mortar sand, lime and cement with and without natural additives.....	62
Figure 34: Compressive strength of mortar Sand and Lime with artificial and natural additives without cement.....	63
Figure 35: Compressive strength of mortar sand, lime and cement with artificial and natural additives with cement.....	64
Figure 36: Resistance to wet and dry cycle - tested mortars compared to untested mortars.....	65
Figure 37: Resistance to salt crystallization- tested mortars compared to untested mortars.....	66
Figure 38: Effect of salt crystallization on mortar without Polymer 1.....	66
Figure 39: Effect of salt crystallization on mortar with polymer 1.....	67
Figure 40: Some pictures show the effect of salt crystallization on Different mortars..	67
Figure 41: Resistance to acid water weathering- tested mortars compared to untested mortars.....	68
Figure 42: Some pictures show the effect of acid water weathering on Different mortars.....	69
Figure 43 : A) SEM of mortar Sand+ lime with polymer 1, B) SEM of mortar Sand+ lime with polymer 2.....	70
Figure 44: (A) SEM of mortar Sand+ lime+ Homraa, (B) SEM of mortar Sand+ lime+ Homraa+ Polymer 1.....	71
Figure 45: (A) SEM of mortar Sand+ lime+ Silica fume, (B) SEM of mortar Sand+ lime+ Silica fume with polymer 1.....	72
Figure 46: (A) SEM of mortar Sand+ lime+ Kosromel with polymer 1, (B) SEM of mortar Sand+ lime+ Kosromel with polymer 2.....	73
Figure 47: (A) Shows Polarized Light; X- 40 of SLC mortar, (B) Shows Crossed Nicols; X- 40 of SLC mortar, (C) Shows Crossed Nicols; X- 100 of SLC mortar.....	75
Figure 48 : (A) Shows Polarized Light; X- 40 of SLCP1 mortar, (B) Shows Crossed Nicols; X-40 of SLCP1 mortar.....	76
Figure 49 : (A) Shows Polarized Light; X-40 of SLCP2 mortar, (B) Shows Crossed Nicols; X-40 of SLCP2 mortar.....	76
Figure 50 : (A) Shows Polarized Light; X- 40 of SLCP3 mortar, (B) Shows Crossed Nicols; X- 40 of SLCP3 mortar.....	77
Figure 51: (A) Shows Polarized Light; X- 100 of SL mortar, (B) Shows Crossed Nicols; X- 100 of SL mortar.....	77
Figure 52 : (A) Shows Polarized Light; X- 40 of SLH mortar, (B) Shows Crossed Nicols; X- 100 of SLH mortar.....	78
Figure 53 : (A) Shows Polarized Light; X- 40 of SLF mortar, (B) Shows Crossed Nicols; X-40 of SLF mortar.....	78
Figure 54: (A) Shows Polarized Light; X-100 of SLP1 mortar, (B) Shows Crossed Nicols; X-100 of SLP1 mortar.....	79
Figure 55 : (A) Shows Polarized Light; X-100 of SLP2 mortar, (B) Shows Crossed Nicols; X-100 of SLP2 mortar.....	79
Figure 56: (A) Shows Polarized Light; X-40 of SLP3 mortar, (B) Shows Crossed Nicols; X-40 of SLP3 mortar.....	80

Figure 57: (A) Shows Polarized Light; X-40 of SLHP1 mortar, (B) Shows Crossed Nicols; X-40 of SLHP1 mortar.....	80
Figure 58: (A) Shows Polarized Light; X-40 of SLKP1 mortar, (B) Shows Crossed Nicols; X-40 of SLKP1 mortar.....	81
Figure 59: (A) Shows Polarized Light; X-40 of SLKP2 mortar, (B) Shows Crossed Nicols; X-40 of SLKP2 mortar.....	81
Figure 60: (A) Shows Polarized Light; X-40 of SLFP1 mortar, (B) Shows Crossed Nicols; X-40 of SLFP1 mortar .....	82

# Abstract

Lime mortar is consist of lime and an aggregate such as sand, mixed with water. It is one of the oldest known types of mortars, dating back to the 4th century BC and widely used in Ancient buildings.

Materials used to repair or replace original Ancient buildings should have similar properties so as not to disrupt the balance of interaction within the building.

The present work is an attempt to improve physical and mechanical properties of lime mortars using different additives.

Lime mortar modified with different additives such as [Homraa, Kosromel, Silica fume, sika bond (polyvinyl alcohol), sika 1 (polyacrylamide) and sikalite (additive 3)] were prepared. Characterization of materials used in mortar preparation are determined by X-Ray diffraction, Chemical analysis, Zeta potential and FTIR.

Different properties of lime mortars were measured: mechanical properties (such as compressive strength) and physical properties (density, porosity and water absorption). These mortars exposed to different environments such as Acid water weathering (using  $H_2SO_4$ ), Salt crystallization (using  $Na_2SO_4$ ) and Wet-dry cycle.

This work is reported that polyvinyl alcohol improve physical and mechanical properties of mortars without cement more than other tested additives. On the other hand when cement added mortar consist of lime, sand, cement and silica fume show high compressive strength than others samples.

# Chapter 1 : Introduction

## 1.1. Background

The traditional lime mortar is consist of lime, sand and water. Besides these constituents it may also contain additives aiming to improve fresh mortar's workability and/or to improve hardened mortars' strength and durability.

The idea of improving mortar's properties by using various additives is not new, but something which has been known already by the first civilizations [1, 2]. Lime-based mortars used in ancient times were sometimes of poor quality; therefore masons were employing various additives to reach desired properties. There are records that egg whites, bullock's blood, fruit juices, keratin and casein were used in Ancient Egypt [3, 4]. Bitumen as an oldest known natural organic additive was used already in Mesopotamia some 4000 years ago [5, 6, 7]. Romans were known to use pozzolanic materials, which were giving hydraulic properties to mortar, but these were not always available and cost was also a large factor [8]. Consequently locally available materials increased in use. Variety of substances of different origin were used, such as local agro products (cereals, juices from trees, fruits and vegetables), oils and fats, milk, eggs, but also blood, dung, urine or other materials like animal hair. Although it looks that almost everything available went into mixes, there seemed to be a method behind their madness [3]. Unfortunately there is not much information in literature about the technology of mortars preparation. This being their live hood, masons were scared to write about the things they knew and often the knowledge and experience were buried with them [6]. On the other side we have legends of excellent durability of some historic mortars, which has been accredited just to the use of natural polymeric additives.

Nowadays it is quite complicated to analyze organic additives in historical mortars since they were probably added in very small amounts which may be under the detection limit of some analytical methods. Thus it is probable that most of the information of using natural polymeric additives is based on the study of historical sources rather than on the exact material analysis of preserved monuments [9].

## 1.2. Thesis objectives

The research objectives of this thesis are:

- To study the effect of additives on the physical and mechanical properties of lime mortars;
- To experimentally verify the assumption that the addition of these additives are increasing mortar's resistance to deterioration;
- To develop a mortar with improved durability suitable for restoration.

# Chapter 2 : Literature Review

## 2.1. Definition of mortar

A mortar can be defined as a mixture of one or more inorganic or organic binders, mostly fine aggregates, water and sometimes additives and/or admixtures in the proportions necessary to give to the mixture proper workability in the fresh state and adequate physical and mechanical properties, outward aspect, durability etc., in the hardened state [10].

Mortar can be divided into:

- According to its use as either:
  - Bedding and jointing mortar – to bond masonry units (brick and/or stones) together;
  - Plastering mortar – for external coating of masonry;
  - Rendering mortar – for internal application on masonry; or
  - Stucco – decoration mortar.
- According to binder (or the combination of binders)
  - Clay mortar;
  - Gypsum mortar;
  - Lime mortar;
  - Pozzolanic mortar;
  - Hydraulic lime mortar;
  - Portland cement mortar;
  - Mixed mortars (lime-clay, lime-gypsum, lime-cement...); or
  - Special mortars (water-proofing, desalination, thermo-insulating mortars...).

## 2.2. Mortar composition

Mortar is composed of a binder, aggregate, water and additives.

### 2.2.1. BINDERS

In general, the purpose of the binder is to hold the sand particles together and to fill the voids in between the grains of sand [11].

### 2.2.1.1. TERMINOLOGY ON LIME

According to the standard EN 459-1 [12] on building lime following terms and definitions apply:

**Lime** - material comprising any physical and chemical forms under which calcium and/or magnesium oxide ( $\text{CaO}$  and  $\text{MgO}$ ) and/or hydroxide ( $\text{Ca(OH)}_2$  and  $\text{Mg(OH)}_2$ ) can appear.

**Building lime** - limes used in building construction and civil engineering. They are either air limes or hydraulic limes.

- **Air lime** – lime mainly consisting of calcium oxide or hydroxide, which slowly harden in air by reacting with atmospheric carbon dioxide. Generally, they do not harden under water as they have no hydraulic properties. They may be either quick lime or hydrated lime.
  - **Quick lime (Q)** - air lime mainly consisting of calcium oxide and magnesium oxide produced by calcination of limestone and/or dolomite rock. They have an exothermic reaction when in contact with water. They are offered in varying sizes ranging from lumps to ground powder materials. They include calcium lime and dolomitic lime.
  - **Hydrated lime (S)** - calcium lime or dolomitic lime, resulting from the controlled slaking of quick lime. They are produced in the form of a dry powder or putty or as a slurry (milk of lime).
  - **Calcium lime (CL)** - lime mainly consisting of calcium oxide or calcium hydroxide without any additions of hydraulic or pozzolanic materials.
  - **Dolomitic lime (DL)** - lime mainly consisting of calcium oxide and magnesium oxide or calcium hydroxide and magnesium hydroxide without any additions of hydraulic or pozzolanic materials.
    - **Semi-hydrated dolomitic lime** - hydrated dolomitic limes mainly consisting of calcium hydroxide and magnesium oxide.
    - **Completely hydrated dolomitic lime** - hydrated dolomitic limes mainly consisting of calcium hydroxide and magnesium hydroxide.
- **Hydraulic lime (HL)** lime mainly consisting of calcium hydroxide, calcium silicates and calcium aluminates produced by mixing of suitable materials. They have the property of setting and hardening under water. Atmospheric carbon dioxide contributes to the hardening process.
  - **Natural hydraulic lime (NHL)** - lime produced by burning of more or less argillaceous or siliceous limestone with reduction to powder by slaking with or without grinding. All NHL have the property of setting and hardening under water. Atmospheric carbon dioxide contributes to the hardening process.
  - **Natural hydraulic lime with additional material (Z)** - special products may contain added suitable pozzolanic or hydraulic materials, up to 20 % by mass, are additionally designated by "Z".