



AIN SHAMS UNIVERSITY
FACULTY OF ENGINEERING
Design and Production Engineering

Assessment of Some Al Alloy Casting Produced by Special Casting Technique

A Thesis submitted in partial fulfillment of the requirements of the degree of
Master of Science in Mechanical Engineering
(Design and Production Engineering)

by

Hassan Mohamed Tiwery

Bachelor of Material Science and Metallurgy Engineering
Faculty of Engineering, Tripoli University 1990

Supervised By

Prof. Adel Badawy El-Shabasy

Prof. Iman Salah El din El-Mahallawi

Dr. Eng. Wael Fathy Hodiafa

Cairo - (2018)



AIN SHAMS UNIVERSITY

FACULTY OF ENGINEERING

Design and Production

**Assessment of Some Al Alloy Casting Produced by Special
Casting Technique**

By

Hassan Mohamed Tiwery

Master of Science In Mechanical Engineering

(Design and Production Engineering)

Faculty of Engineering, Ain Shams University, 2018

Examiners' Committee

Name and Affiliation

Signature

Prof.Dr. Tamer Samir Mahmoud

.....

Design and production, Benha University.

Prof.Dr. Ahmed Mohamed Moneeb Elsabbagh

.....

Design and Production , Ain Shams University.

Prof.Dr. Adel Badawy El- Shabasy

.....


Design and Production , Ain Shams University.

Prof.Dr. Iman Salah El din El- Mahallawi

.....

Mining and Petroleum and Metallurgy, Cairo University.

29 / 3 / 2018



AIN SHAMS UNIVERSITY

FACULTY OF ENGINEERING

Design and Production

**Assessment of Some Al Alloy Casting Produced by Special Casting
Technique**

By

Hassan Mohamed Tiwery

Master of Science in Mechanical Engineering

(Design and Production Engineering)

Faculty of Engineering, Ain Shams University, 2018

Supervision' Committee

Name and Affiliation

Signature

Prof.Dr. Adel Badawy El- Shabasy
Design and production Engineering, Ain Shams
University

.....

Prof.Dr. Iman Salah El din El- Mahallawi
Mining and Petroleum and Metallurgy Engineering,
Cairo University

.....

Dr. Eng. Wael Fathy Hodiefa
Mining and Petroleum Engineering, Al-Azhar University

.....

29 / 3 / 2018

Statement

This thesis is submitted as a partial fulfillment of Master of Science in Mechanical Engineering, Faculty of Engineering, Ain shams University.

The author carried out the work included in this thesis, and no part of it has been submitted for a degree or a qualification at any other scientific entity.

Signature

.....

Hassan Mohamed Tiwery

Date: 29 / 3 / 2018

Researcher Data

Name : Hassan Mohamed Tiwery

Date of birth : 12/12/1966

Place of birth : Tripoli, Libya

Last academic degree : Bachelor Degree

Field of specialization : Material science& Metallurgy engineering

University issued the degree : Tripoli University

Date of issued degree : January, 1990

Current job : Teaching Assistant, Mechanical Engineering Department, Academic Engineering, Tajura, Tripoli, Libya.

ACKNOWLEDGEMENT

All thanks and indebted first, to Allah, who guided and helped me to go through and finish this work.

I would to express my appreciation and gratitude to the supervisors **Prof. Dr. Adel Badawy El- Shabasy & Prof. Dr. Iman Salah El-Mahallawi & Dr. Wael Fathy Hodiefa** for their sponsorship, enthusiastic guidance and valuable discussions.

My cordial second thanks are due to his Excellency **Dr. Wael Fathy Hodiefa** supervisor casting lab of Mining & Petroleum Dep. Faculty of Engineering. Al-Azhar University, his generous assistance in facilitating equipment, laboratories and encouraging me to complete this thesis and all support during the experimental work.

My great appreciation for **all the member** of labs metallurgy & petroleum Dep. Faculty of Engineering. Cairo University for their help and support during the experimental work.

My thanks **the Regional for Center of Mycology and Biotechnology**, Azhar University, Cairo, Egypt. For SEM & TEM, and also **Eng. Youssef Ali** in mechanical & production Dep. Faculty of Engineering. Cairo University.

All my love and gratitude are due to my **Mother, Wife and my Children**. I'm really appreciated their kindness and creating a good atmosphere during this study.

ABSTRACT

The main objective of this work is to study the enhancement of microstructure & mechanical properties of A356/ZrO₂ Metal Matrix nano composites. For completing such study different treatments were executed for the additives at different volume fraction using stir casting technique. Also heat treatment affected the fabricated composites was studied.

Recent investigation has-been divided into three parts:

Part I: This section describes the effect of using different nanoparticles feeding routes (direct, capsule & regular) treatments of nanoparticles (as additives) on the microstructure and mechanical properties of A356 alloy.

A number of cast samples of A356 alloy were prepared by rheo-casting in a specially designed and built resistance furnace unit allowing feeding ZrO₂ nano- particles (30nm) in to the slurry in the semi-solid state with mechanical stirring at constant parameter (temp stirring 595-610°C, stirring speed 670 r.p.m at stirring time 2 minute).

Part II: This section presents the effect of different weight% of nano particles addition (1%, 2%, 3%, 4% & 5%) on the microstructure and the mechanical properties of the nano ZrO₂ reinforced A356 cast alloy.

Part III: This section presents the results obtained in this work for the microstructure and mechanical properties of capsule feeding 3% ZrO₂ nanoreinforced A356 alloy with compare to monolithic cast A356 alloy in T6 heat treated condition. The samples were solution treated at temperature of 550°C for 2 hours, followed by aging at different temperatures (170°C&180°C), for different aging times (2, 4 & 6 hours).

The results showed that microstructure of the nano composite samples revealed grain refinement in aluminum matrix support dendrite and inter lamellar spacing in the eutectic silicon phase for the nano composite ZrO_2 . The capsule treated feeding at 3% ZrO_2 alloy has the best mechanical properties (Strength 165MPa, %Elongation 4.7& Hardness 60 HRB), compared to monolithic cast alloy (Strength 119MPa, %Elongation 4.5& Hardness 23 HRB). The heat treatment T6 produced for capsule feeding 3% ZrO_2 Alloy result has better than monolithic casted alloy (Strength from 119MPa to 198MPa, %Elongation from 4.5 to 6.4 , Hardness from 23 to 70 HRB), an effective change on morphology of the eutectic silicon lamellae. More details discussed using SEM and EDX analysis.

The nano-composites exhibited better mechanical properties when compared with the A356 monolithic alloy, also the addition of 3% ZrO_2 nanoparticles, and heat treated T6 process has the best result in mechanical properties.

Key words:

Aluminum alloy, stirring casting, ZrO_2 nanoparticles, strength, hardness, heat treatment.

CONTENTS

	Page No
Acknowledgement	I
Abstract	II
Contents	IV
List of figures	VII
List of Tables	XII

Chapter1

Introduction:

1.1	Motivation	1
1.2	Background	2
1.3	Aim and objective	3

Chapter 2

Literature Review

2.1	Introduction	4
2.2	Classification of Aluminum alloys	4
2.2.1	Wrought alloy	4
2.2.2	Casting alloys	5
2.2.3	Al- designation system	5
2.3	Aluminum Silicon Alloys	6
2.4	Methods of enhancing properties of Al-Si alloys	8
2.4.1	Effect of modification	8
2.4.2	Effect of Grain Refining	10
2.4.3	Effect heat treatment T6	11
2.4.4	Strengthening by dispersion of micro and nano Particles	14
2.5	Metal Matrix Composites	15
2.5.1	Liquid State Processing	16
2.5.1.1	Stir casting	16
2.5.1.2	Squeeze casting	17
2.5.2	Solid State Processing	18
2.5.3	Deposition Process	18
2.5.4	Semisolid State Processes	18
2.6	Nano reinforced composites	19

2.6.1	Nanoparticles	19
2.7	Processing techniques of MMNCs	20
2.7.1	Stir casting technique	21
2.7.2	Compo casting process	21
2.8	Factors affecting cast metal matrix composites	22
2.8.1	The distribution of additives materials	22
2.8.2	Porosity in cast metal matrix composites	23
2.8.3	Wettability between the matrix alloy and Particle Additives in MMCs	24
2.8.4	Interfacial chemical reaction	25
2.8.5	Factor affecting mechanical properties of Metal Matrix nano Composites by stir casting technique	26
2.8.5.1	Particle size	27
2.8.5.2	Additives weight fraction	27
2.8.5.3	Stirring speed	28
2.8.5.4	Stirring Temperature	29
2.9	Influence of ZrO₂ particles and process Parameters On the mechanical properties of A356 by stir casting Process MMCs	30

Chapter 3

Experimental Work:

3.1	Introduction	34
3.2	Materials System Selection	35
3.2.1	Matrix Alloy	35
3.2.2	Additives Materials	36
3.3	Material casting and preparation	38
3.3.1	Casting technique	38
3.4	Material Characterization	43
3.4.1	Sample preparation	43
3.4.2	Microstructure Evaluation	43
3.4.2.1	Optical Microscope (OP)	44
3.4.2.2	Scanning electron microscope (SEM)	44
3.4.2.3	Transmission electron microscope (TEM)	44
3.4.3	Mechanical Characterization	47
3.4.3.1	Tensile Test	47

3.4.3.2 Hardness Test	49
3.5 Ageing Treatment	49

Chapter 4

Result and Discussion:

4.1 Effect of Particulate Feeding Methods on Microstructure and Mechanical Properties of A356/ZrO ₂ Nano-reinforced Composite	52
4.1.1 Microstructural Evolution	53
4.1.2 Mechanical properties	57
4.2 Effect of Nanoparticles% of Microstructure And Mechanical Properties of A356/ZrO ₂ Nano- reinforce Composites	63
4.2.1 Microstructural Evolution	63
4.2.2 Microstructural Parameter	66
4.2.3 Mechanical properties	71
4.3 The Effect of Heat Treatment on Microstructure and Mechanical properties of capsule treated feeding 3% ZrO ₂ nano-reinforced to A356 alloy Composites	76
4.3.1 Microstructural observation of the cast samples	76
4.3.2 Microstructural observation of the cast samples	78
4.3.3 Effect of artificial ageing temperature & Ageing Time on hardness	82
4.3.4 Effect of (T6) heat treatment on tensile strength And hardness of A 356 Alloy	84

Chapter 5:

Conclusion	89
------------	----

References:	91
-------------	----

LIST OF FIGURES

Figure No	Title	Page No
(2.1)	Al-Si phase diagram.....	6
(2.2)	Commercial cast aluminum-silicon all microstructures (a) hypoeutectic alloy (1.65- 12.6 wet% Si), (b) eutectic alloy (12.6%Si), and (c) hypereutectic alloy(>12.6%Si).....	7
(2.3)	Comparison of the silicon morphology in: (a) unmodified (b) Sr-modified (300 ppm Sr); and (c) Sb-modified (2400 ppm Sb), hypoeutectic aluminum-silicon alloys.....	9
(2.4)	SEM microphotographs of Al-7Si alloy (a) without grain refiner (b) with grain refiner (1% of M13), (c) with modifier (0.02% Sr) and (d) with grain refiner (1% of M13) and modifier (0.02% Sr).....	11
(2.5)	Diagram showing the step of the T6 heat Treatment alloy.....	12
(2.6)	Artificial aging for A356 after solution treatment at 540°C 6hr water quenched and at Arterial aging at different temp.....	13
(2.7)	Max hardness value after solution treatment 540°C at different temperatures 160°C, 180°C, And 190°C.....	13
(2.8)	Effect of micro/submicrometre additions on (a) Ultimate tensile strength (UTS) and (b) elongation per cent of A356 processed in Semisolid state.....	14
(2.9)	Stir casting (vortex).....	17
(2.10)	Squeeze casting technique.....	17
(2.11)	Design Setup of Compo Casting.....	22
(2.12)	Schematic diagram showing the contact angle Between a liquid and solid surface. When (a) θ $= 0^\circ$ —perfect wettability, (b) $\theta = 180^\circ$ — Wetting, (c) and $0^\circ < \theta < 180^\circ$ —partial wetting...	25
(2.13)	Effect of nano- additions on UTS, hardness and	

	% elongation of A356.0, using ZrO_2 (40 nm).....	28
(2.14)	The effect stirring speed on UTS with 3% ZrO_2 at 600°C.....	29
(2.15)	The effect of stirring temperature on the UTS of MMC at 3% fraction of ZrO_2 nano particles at 1500 r.p.m stirring speed.....	30
(3.1)	Preparation of casting alloys.....	34
(3.2)	Characterization of casting alloys.....	35
(3.3)	SEM micrographs ZrO_2 (30 nm).....	37
(3.4)	TEM micrographs of (30) nm ZrO_2 particles.....	37
(3.5)	Casting unit used for the production of MMNCs ; (a) casting furnace, (b) Stirring motor, (c) Furnace cover, (d) crucible, (e) axial-flow impeller with 3 blades, (f) stainless- steel casting mold (g) pouring and (h) fabricate cast.....	40
(3.6)	Mold design (a), stirrer design (b), crucible design (c).....	41
(3.7)	Grinding and polishing rotating disc located at metallurgy & petroleum Dep Cairo University Egypt.....	45
(3.8)	Olympus BX41M-LED metallurgical microscope System.....	45
(3.9)	Jeol (JSM-5500 LV) located at Regional Center of Mycology an Biotechnology, azhar University, Cairo, Egypt.....	46
(3.10)	(Spi-Mo dule sputte- coater) located at Regional Center of M cology Biotechnology, azhar University, Cairo, Egypt.....	46
(3.11)	(jeol-1010) by using high vacuum mode at 80KV located Regional center of mycology and Biotechnology Azhar University, Cairo.....	47
(3.12)	ASTM tensile test (B557M-060).....	48
(3.13)	Monstant universal Testing.....	48
(3.14)	Rockwell hardness located at production and design Dep Cario University.....	49
(3.15)	Elctrical (a) furnace of (1200° C) , and (b) ageing treatment located at mining & pet Dep, Al-Azhar University, Egyp.....	50
(3.16)	Heat treatment procedures.....	51

(4.1)	Optical micrographs of A356.0 aluminum alloy that cast in liquid state at 700°C at X100 magnifications.....	53
(4.2)	Optical micrographs of A356 aluminum alloy that cast in liquid state at 700°C (a) & Optical micrographs of A356+3% ZrO ₂ semi solid state at 610°C in (b) capsule feeding magnification....	54
(4.3)	SEM micrograph of cast A356, at 700°C (a) X700 (b) X2200, magnification.....	55
(4.4)	SEM micrograph of the micro structure of (A356/3% ZrO ₂) semi solid treated at 610°C, flake lamellae eutectic Si (a) non-homogenous distribution of the particles and clustering and agglomeration of the ZrO ₂ particles within the matrix alloy (b, c, d) at different magnification....	55
(4.5)	SEM micrographs of the 3% ZrO ₂ particles Showing nanoparticles agglomeration at the Si particles of the eutectic structure, at (a) X1200, (b) X17000, (c) X27000, (d) X35000.....	56
(4.6)	EDX spectrum of (A356/3% ZrO ₂) with gold foil etching.....	56
(4.7)	Change in UTS with nanoparticles (capsule, regular & direct) treated feeding.....	58
(4.8)	Variation of Elongation% with nanoparticles (direct, capsule & regular) treated feeding.....	59
(4.9)	Variation of hardness with nanoparticles (direct, capsule regular) treated feeding.....	60
(4.10)	Optical micrographs of A356.0 aluminum alloy that cast in liquid state at 700°C (a) & Optical micrographs of A356.0 /3% ZrO ₂ semi solid state at 610°C in (b) direct feeding, (c) regular feeding (d) capsule feeding at X 200 magnification.....	64
(4.11)	SEM micrograph of cast A356, flake lamellae eutectic Si & α-Al phase at 700°C (a) X700, (b) X2200, magnification. SEM Micrograph of the micro structure of (A356/3% ZrO ₂) semi solid treated at 610°C, non-homogenous	

	distribution of the particles and clustering agglomeration ZrO_2 particles within the matrix alloy (c & d).at magnification (c) X7000, (d) X8000.....	65
(4.12)	SEM&EDX spectrum of (A356.0/3% ZrO_2) with gold foil etching at X1200.....	65
(4.13)	Microstructure features of cast Al alloy at 700°C, at X100 magnification.....	66
(4.14)	Microstructure features of A356/3% ZrO_2 nanoparticles direct feeding semi solid state at 610°C stirring time of 2 min, stirringspeed rpm at X100 magnification.....	67
(4.15)	Microstructure features of A356/3% ZrO_2 nanoparticles regular feeding semi solid state at 610°C stirring time of 2 min, stirring speed 670 rpm at X100 magnification.....	67
(4.16)	Microstructure features of A356/3% ZrO_2 nanoparticles capsulate feeding semi solid state at 610°C stirring time of 2 min, stirring speed 670 rpm at X10 magnification.....	67
(4.17)	Influence of % ZrO_2 nanoparticles addition (as A356 cast alloy)and (capsulate, regular& direct) treated feeding on inter-lamellar spacing (μm).....	70
(4.18)	Influence of % ZrO_2 nanoparticles (as A356 Cast alloy) and(Capsulate, regular & direct Treated feeding on dendrite arm length (μm)).....	70
(4.19)	Change in UTS with nanoparticles (capsulate, regular& direct) treated feeding.....	73
(4.20)	Variation of Elongation% with nanoparticles (direct, capsulate & regular) treated feeding.....	74
(4.21)	Variation of hardness with nanoparticles (direct, capsulate & regular) treated Feeding.....	75
(4.22)	Optical micrographs of A356.0 aluminum alloy as cast alloy from the liquid state 700°C &A356 +3% ZrO_2 cast from the semi-solid state at 610°C capsulate feeding at 100 magnification.....	77
(4.23)	SEM Micrograph of cast A356.0, flake	