



شبكة المعلومات الجامعية

بِسْمِ اللَّهِ الرَّحْمَنِ الرَّحِيمِ





شبكة المعلومات الجامعية



شبكة المعلومات الجامعية

التوثيق الالكتروني والميكرو فيلم

جامعة عين شمس

التوثيق الالكتروني والميكرو فيلم

قسم

نقسم بالله العظيم أن المادة التي تم توثيقها وتسجيلها
علي هذه الأفلام قد اعدت دون أية تغيرات



يجب أن

تحفظ هذه الأفلام بعيداً عن الغبار

في درجة حرارة من 15 – 20 مئوية ورطوبة نسبية من 20-40 %

To be kept away from dust in dry cool place of
15 – 25c and relative humidity 20-40 %



شبكة المعلومات الجامعية



بعض الوثائق الأصلية تالفة



شبكة المعلومات الجامعية



بالرسالة صفحات
لم ترد بالأصل



**BENEFICIATION OF MANGANESE FROM ITS
ORES PRESENT IN ARAB REPUBLIC OF
EGYPT USING SOME REDUCTANTS**

A Thesis Presented

By

Abd El kader Mohamed El Maghraby

(B.Sc.Chemistry , 1985)

(Diploma , Analytical Chemistry , 1989)

(M.Sc. Chemistry , 1994)

Assuit University

For

The Degree of Doctor of Philosophy in Science

(Chemistry)

Supervised By

Prof. Dr. R.M. Awadallah

Prof. of Anal. and Inorg Chem.

Faculty of Science

Aswan

South Valley University

Prof. Dr. M.T.El Haty

Prof. Of Inorg. Chem.

Vice Deán – Faculty of Science

Aswan

South Valley University

Dr. M.A.El Taher

Lecturer of Physical Chemistry

Aswan - Faculty of Science

South Valley University

To

Chemistry Department , Aswan-Faculty of Science

South Valley University

1419-1999

B 119

ACKNOWLEDGEMENT

ACKNOWLEDGEMENT

All thanks are given to **ALLAH** who gave me spirit and help. The author wishes to express his deepest thanks, gratitudes and gratefull appreciation to **Prof. Dr. R.M. Awadallah**, Professor of Analytical and Inorganic Chemistry, Faculty of Science at Aswan, South Valley University, Assawn Branch, for suggesting the plan of research, the solution, valuable directions, sincere supervision, facilities, advices, generous help, keen continuous interest, faithful encouragement, significant discussion and valuable interpretation and continuous guidance throughout the whole work from the beginning until the submission of this thesis. Also the author wishes to thank **Prof. Dr. M. Tawfik – El Haty** professor of Inorganic Chemistry and Vice Dean, Faculty of Science, South Valley University for Significant encouragement and helps. Also the author wishes to thank **Dr. M.A. El Taher**, Lecturer of physical chemistry, Chemistry, Department, Aswan Faculty of science, South valley university, for his significant encouragement, facilities and sincere unfailing help. **Prof. Dr. M.A. El Maghraby**, The Dean of Aswan Faculty of Science, and Prof. **Dr. A.I.M. Koraiem**, the Vice Dean for Postgraduate Studies and Research are appreciated and acknowledged. The author would also like to express for his respects and appreciations to **Mr. M. Salah Rostom**, Laboratory Chief, **Mr. M. Hariedy**, Chief of Quality Control, Arab Company for special steel. My thanks are also given to **Dr. S.A. Abd El Aal**, Assistant Professor of Hydrometallurgy in R & D, Helwan - Eltabbin and **Dr. E- Abd El Rahman**, Aluminum Company of Egypt. My thanks are also given to my colleagues in Egyptian Ferroalloys Company and Arab Company for Special Steel. (Arcosteel). My thanks are also given to every body who helped or encouraged me during this work. Finally my deep thanks are also due to my parents, my wife and to the all members of my family.

The Author

A.M. El Maghraby

ABSTRACT

Title:-

“ BENEFICIATION OF MANGANESE FROM ITS ORES PRESENT IN ARAB REPUBLIC OF EGYPT USING SOME REDUCTANTS ”

Author :

A.M. El Maghraby , Chemist in Arab Company for Special Steel

Place of Research :

Egyptian Ferroalloyes Company Laboratory, Edfu Aswan Governorate.

The present work deals with the application of reduction leaching process to the extraction of manganese from Egyptian fine manganese ore wastes by the aid of metallurgical wastes in the Egyptian Ferroalloys Company. In this technique, metallurgical coke, semi coke, charcoal, pure and impure sugars, starch, molasses, scum and hydrogen peroxide were utilized as reductants in sulphuric acid medium. The optimum conditions of the process are : (120 mesh ore particle size and minus 200 mesh reductant particle size, 6% ore : H_2SO_4 ratio in the case of metallurgical coke, semi coke and charcoal , minus 100 mesh ore particle size and 10% ore : H_2SO_4 ratio in the case of pure, impure sugars, starch, molasses, scum and hydrogen peroxide) 90, 90, 90, 60, 60, 70, 70 ,80 and 60 minutes leaching time, 90, 90, 90, 90, 90, 90, 90, 90 and 60 C leaching temperature ,25 ,25, 20, 20, 20, 25, 30, 30 and 15% H_2SO_4 , 5:1 , 4:1, 3:1, 1:1, 2:1, 2.5:1, 3:1, 4:1 and 1.6:1 reductant : MnO_2 ratios. The percentage recoveries equal 86.5, 93, 98.6, 91.5, 100, 100, 96, 90.5 and 96.2% in the case of metallurgical coke, semi coke, charcoal, pure, impure sugars, starch, molasses, scums and hydrogen peroxide, respectively.

Also , the optimum conditions were applied using electrode paste before and after usage , graphite electrode after usage , dried scum before and after chairring, pure and impure sugar after, chairring., The percentage of manganese recoveries are : 21.11 , 12.15 , 26.2 , 75, 90.5 , 96.92 and 93.78% respectively. Also, the effect of differrent ores origin of, Elba ,(A),(B),(C), Sinai (A),(B) and FeMn slag was studied. The percentage of manganese recoveries equals (77,76.2,75,73.4,70 and 100% Mn) in case of mefallurgical coke,(80,79.11,78,75,72 and 100%) Mn) in case of semi coke, (81.5,80.6,78,86.5,73.6 and 100% Mn) in case of charcoal (100,100,99.3,98.7,96.8 and 100% Mn) in case of pure sugar, (100,97.1,97.9,96,95 and 100%Mn) in case of impure sugar, (98.6, 96,95,95.5,93.5 and 100% Mn) in case of starch, (96,94,93.6,92,90and 100% Mn) in case of Molasses and (90.5, 91, 91, 90, 88.4 and 100% Mn) in case of scum, using Elba (A), (B) and (c) Sinai (A) , (B) and FeMn slag respectively as a diffrent ore origin . Also hydrochloric acid was used with the same reductant and the extraction percent of manganese equals 100% but hydrochloric acid not permitted because of its high price and high consumption. Manganese separated as MnO. MnO equals 98 and 97% on using KOH and Na₂CO₃ as precipitating agents,

CONTENTS

Subject	Page
(CHAPTER I)	1-27
(INTRODUCTION , GEOLOGY OF THE AREA AND LITERATURE SURVEY)	
INTRODUCTION	1
◆ Classification of Processes and Equipments	1
◆ Wastes of Ferromanganese Industry	1
◆ Classification of Manganese Minerals	2
◆ Occurrence of Egyptian Manganese Ores	2
◆ Geology of the Elba Pyrolusite Ores	2
◆ Geology of Sinai Peninsula	3
◆ Origin of Coal	4
Charcoal	4
◆ Literature Survey	5
(CHAPTER II)	28-59
◆ EXPERIMENTAL	
(1) Samples, Collections and Preparation of Representative Sample	28
(A) Elba (A) Pyrolusite Ore :	28
(B) Sinai Pyrolusite Ore :	28

Subject :	Page
(C) Reductants :	29
(2) Working Procedure :	29
(I) Effect of Sulphuric Acid on Leaching Elba (A)	
Pyrolusite Ore	29
(A) In Absence of Reducing Agents	29
(1) Effect of Sulphuric Acid Concentration.....	29
(2) Effect of Ore : H ₂ SO ₄ Ratio.....	30
(3) Effect of Leaching Temperature.....	30
(4) Effect of Leaching Time	30
(5) Effect of Ore Particle Size.....	30
(B) In Presence of Reducing Agents.	30
(I) ♦ <u>Using Metallurgical Coke , Semi Coke and Charcoal</u>	
(1) Effect of Ore Particle Size.	31
(2) Effect of Leaching Time.....	31
(3) Effect of Leaching Temperature.	31
(4) Effect of Reductant : MnO ₂ Ratio.	31
(5) Effect of Sulphuric Acid Concentration.	32
(6) Effect of Reductant Particle Size	32